



SLATE LITE™

# Slate-Lite 2K-Protection Wall

Data sheet

06.02.2017

## PRODUCT DESCRIPTION

*Slate-Lite 2K-Protection Wall* is a two-component (component 1: 500g / component 2: 125g) and air-drying sealing. It has a short drying time, is easy to clean and has a hard surface.

## APPLICATION AREAS

High traffic walls, for example in showers, furniture, backsplashes.

## INSTRUCTIONS

Mix component 1 and 2 in the ratio 4:1. Process the mixture within 3–4 hours after mixing. Apply the *Slate-Lite 2K Protection Wall* with a sponge roller or paintbrush. After completion clean your tools immediately to avoid damage.

## HEAT RESISTANCE

Outstanding heat resistance up to 160°C (no gloss reduction, no other quality losses; from about 120°C, however, depending on color, slight color variations possible).

## DRYING TIME

Minimum processing temperature 10°C, ideal temperature 20°C, do not process at more than 30°C. Dust-dry after 15–30 minutes, touch dry after 60–120 minutes. Thoroughly dried after 5–10 hours.

## CLEANING

*Slate-Lite 2K-Protection Wall* can be maintained well with most commercially available cleaners.

## REMARKS

This sealing can be reapplied without sanding the previous layer. Please be aware of the color darkening of the material when applied.

## TECHNICAL DATA

Color  
transparent

Firing point  
approx. 25°C (DIN 53213)

Ignition temperature  
> 240°C (DIN 51794)

Density at 20°C  
approx. 1

Solubility in water at 20° in %  
insoluble (< 3)

Viscosity in Sec. at 20°C  
approx. 120

### NOTE

This information and our technical advice whether spoken, written or through attempts are made to the best of knowledge. However, they apply only without warranty. This applies also to proprietary rights of third parties. This advice does not release from own tests of our products and advices to their suitability of your own projects and purposes. In addition to our information, the relevant guidelines and advices of organizations and trade associations as well as the DIN standards must be observed. The application, use and processing of our products and the products based on our technical recommendations are beyond our control and, therefore, entirely within your own responsibility.